

Tubing Specifications



Tubing Specifications LLDPE

Tubing, 3/8"ID x 1/2"OD, Natural		Tubing, 1/4"ID x 3/8"OD, Natural	
E00001	20' roll	E00002	20' roll
E00001-00	by the foot	E00002-00	by the foot
E00001-50	50' roll	E00002-50	50' roll
E00001-100	100' roll	E00002-100	100' roll
E00001-250	250' roll	E00002-250	250' roll
E00001-500	500' roll	E00002-500	500' roll


Tubing, 3/8"ID x 1/2"OD, Black, UV Resistant		Tubing, 1/4"ID x 3/8"OD, Black, UV Resistant	
E00074	by the foot	E00075	by the foot
E00074-500	500' roll	E00075-500	500' roll

Linear Low Density Polyethylene Plastic Tubing - LLDPE

I.D. = Inside Diameter
O.D. = Outside Diameter

Sizes			Working
I.D. Sizes	O.D. Sizes	Wall Thickness	PSI @ 73°F
1/4	3/8	1/16	214
3/8	1/2	1/16	153

Temperature vs. Working Pressure Relationship of LLDPE



Temperature directly affects the strength properties of LLDPE. As the liquid or atmospheric temperatures rise, the pressure capability of tubing decreases rapidly. The chart shows an approximation of this relationship.

WALCHEM

IWAKI America Inc.

Buy: www.ValinOnline.com | Phone 844-385-3099 | Email: CustomerService@valin.com

Specifications

LLDPE Polyethylene Tubing (Natural and Black)

Properties	Units	Typical values (1) (S.I.)
Melt Index	g/10 min	0.69
Density	g/cc	0.9216
Tensile Yield	MPa PSI	9.5 1380
Tensile Strength	MPa PSI	21.8 3160
Tensile Elongation	%	780
Flexural Modules	MPa PSI	333 48.200
Flexural Strength	MPa PSI	13 1890
Izod Impact		No Breaks
ESCR - Condition B	Hours	336 with no failures
Condition C	Hours	336 with no failures

(1) Typical Values represent average laboratory values and are intended as guides only, not as specific specification limits.

(2) Properties designated have been determined in accordance with the current issues of the specified testing methods.

Methods of the American Society for Testing and Materials (ASTM) are used whenever applicable.

LLDPE 1000 complies with the specifications contained in U.S.A. Food and Drug Administration (FDA) Regulation 21 CFR 177.1520 for Olefin Polymers, para. (c) 3.1 and 3.2 and thus may be used in contact with food as described in the Regulations.

Neither Iwaki America, the manufacturer, nor it's marketing affiliates shall be responsible for the use of this information or of any product, method or apparatus mentioned. You must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product, and nothing herein waives any of the Sellers conditions of the sale.

ABOUT US

Walchem integrates its advanced sensing, instrumentation, fluid pumping and communications technologies to deliver reliable and innovative solutions to the global water treatment market.

Our in-house engineering is driven by quality, technology and innovation. For more information on the entire Walchem product line, visit: www.walchem.com



Walchem, Iwaki America Inc.
Five Boynton Road Hopping Brook Park
Holliston, MA 01746 USA
Phone: 508-429-1110 www.walchem.com

P/N 180621.A

